

ABSTRACT OF THE DISCLOSURE

5 A heat-softening heat-radiation sheet including a polyolefin-based heat-conductive composition which comprises a polyolefin and a heat-conductive filler, has a softening point of 40°C or above, has a thermal conductivity of 1.0 W/mK or higher, has a viscosity at 80°C of from 1×10^2 to 1×10^5 Pa·s and has a plasticity at 25°C in the range of from 100 to 700. This heat-radiation sheet which is in the form of a solid sheet at
10 room temperature, can readily be attached to or detached from electronic components and a heat sink, is capable of softening by the heat generated during operation of electronic components, to have the interfacial contact thermal resistance at a negligible level, and has a superior heat-radiation performance.

15

TOP SECRET